

MP Wax Standard Wax

Product Description

Specially formulated to print at a wide range of energy and speed settings, MP wax provides an economical solution for everyday thermal transfer printing. It incorporates technology designed to control and dissipate static charges and a backcoat proven to protect your printhead. This wax ribbon features a blend of ingredients that are combined in an ink that prints dark images and crisp, clean barcodes.

Recommended Applications



Inventory & Logistics



Retail



Food & Beverage

Recommended Substrates

Paper

Coated paper
Coated tag
Uncoated paper
Uncoated tag

Performance Characteristics

- ▶ Halogen-free
- ▶ High-density
- ▶ High-speed
- ▶ Made in U.S.A.
- ▶ Scratch Resistant
- ▶ Smudge Resistant



for more info!

MP Wax Standard Wax

Ribbon Properties

Description	Result	Test Method
Ink	Wax	
Color	Black	Visual
Total Thickness	7.8 ± 0.6μ	Micrometer
Base Film Thickness	4.8 ± 0.3μ	Micrometer
Ink Thickness	3.0 ± 0.3μ	Micrometer
Ink Transfer Temperature	Uncoated tag 67°C (152°F)	Differential Scanning Calorimeter

Durability of Printed Image

Label Stock: Fasson 1C

Print Speed: 6 IPS

Description	Result	Test Method
Print Density	> 1.75	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 50 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 20 Cycles @ 200 Grams with Stainless Steel Pointed Tip

*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.

Conversion Chart

Millimeters (mm) to Inches = mm ÷ 25.4	Inches to Millimeters (mm) = Inches ÷ 0.03937
Meters (m) to Feet (ft) = m ÷ 0.3048	Feet (ft) to Meters (m) = Feet ÷ 3.2808
C° to F° = (1.8 X C°) + 32 = F°	F° to C° = (F° ÷ 1.8) - 17.77
Thousand square inches (MSI) to m ² = MSI X 0.645	MSI = m ² ÷ 0.645



The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.