DNP Technical Data Sheet

TR6080High Performance Wax/Resin

Product Description

TR6080 is a versatile ribbon that prints on a wide variety of substrates. It provides superior scratch and smudge resistance on paper and synthetic substrates and provides durability comparable to resin ribbons on select labels.

Recommended Applications













Automotive

Health & Beauty Inventory & Logistics

Outdoor

Pharmaceutical

Retail

Recommended Substrates

Paper	Gloss paper
Economy Synthetics	Polypropylene
	Top-coated vinyl
	Polyethylene
	Polystyrene
	Polyolefin
Specialty Materials	Coated/uncoated Valeron®
	Tyvek®
	Tyvek Brillion®
	Coated/uncoated V-max®

Performance Characteristics

- > Prints on a wide variety of substrates from rough label stocks to high-gloss paper
- Prints at high speeds (up to 12 IPS)
- Enhanced smudge and scratch resistance
- High performance backcoat protects the printhead
- Unbeatable edge definition for dark, dense images and improved scan rates
- Excellent durability





DNP Imagingcomm Europe B.V Oudeweg 42, 2031CC Haarlem, the Netherlands T: +31 (0)23 553 30 60 E: sales.emea@dnp-g.com eu.dnpribbons.com

DNP Technical Data Sheet

TR6080 High Performance Wax/Resin

Ribbon Properties

Description	Result	Test Method
Ink	Wax/Resin	
Color	Black	Visual
Total Thickness	8.2 ± 0.5µ	Micrometer
Base Film Thickness	$4.8 \pm 0.3 \mu$	Micrometer
Ink Thickness	$3.4 \pm 0.2 \mu$	Micrometer
Ink Melting Point	75°C (167°F)	Differential Scanning Calorimeter

Durability of Printed Image

Label Stock: Fasson 1C	Print Speed: 6 IPS	
Description	Result	Test Method
Print Density	> 1.80	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 50 cycles of 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 20 cycles of 200 Grams with Stainless Steel Pointed Tip
*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent,		ade Levels A, B, C, D, and F, where A is excellent,

*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.

Conversion Chart

- 11		
I	Millimeters (mm) to Inches = mm ÷ 25.4	Inches to Millimeters (mm) = Inches \div 0.03937
I	Meters (m) to Feet (ft) = $m \div 0.3048$	Feet (ft) to Meters (m) = Feet ÷ 3.2808
I	C° to $F^{\circ} = (1.8 \times C^{\circ}) + 32 = F^{\circ}$	F° to C° = (F° ÷ 1.8) - 17.77
l	Thousand square inches (MSI) to $m^2 = MSI \times 0.645$	$MSI = m^2 \div 0.645$

Compliance Certifications



The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

DNP Imagingcomm Europe B.V Oudeweg 42, 2031CC Haarlem, the Netherlands T: +31 (0)23 553 30 60 E: sales.emea@dnp-g.com eu.dnpribbons.com